



Example of my Magless

Magless 2021 Sherilyne Dougherty

Painted clear Tekta 3mm glass with green Color Line paint. Let dry for 24-48 hours.
I used copper wire-made loops on each end-bent in the middle and over the piece.
Pinched with flat nosed jewelry pliers.
Put a dab of glue on back to hold wire in place
Let dry 24 hours.

Firing Schedule:

450°/hour – 800° – hold 20 min.
450°/hour – 1100° – hold 20 min.
600°/hour – 1485° – hold 15 min.
Full – 950° – hold 60 min.

After firing polished with wire brush to bring the luster back to the copper wire – the best I could. Still needs some polishing.